





Alumanate Architectural

Alumanate is dedicated to the manufacturing of aluminum composite material (ACM) for building, construction and signage applications.

Regardless if you're an architect, designer, fabricator or installer, we are committed to helping you overcome your project challenges and ultimately achieve your vision with beautiful and affordable aluminum composite material. Our stylish and functional cladding solutions for both interior and exterior applications will bring durability paired with pristine looks for years to come.

Product Availability

Alumanate Architectural panels are available in various sizes such as 48", 50" and 62" wide, and lengths of 96", 120", 146" and 196". With multiple warehouse locations across the United States, Alumanate is the largest stock-holder of ACM in the country.

Specialty Finishes

From textured wood grain to sand stone and granite, Alumanate has over 30 stock colors and textures to choose from. In addition, we specialize in custom color matching and design.





Product Information

Alumanate Architectural ACM is composed of two sheets of aluminum bonded to either a mineral-based FR (fire resistant) or PE (polyethylene) core. Alumanate Architectural ACM can be used for many applications such as exterior and interior cladding, column covers, canopies and even clean rooms. The versatile nature of Alumanate Architectural ACM enables architects to deliver inspiring, original and innovative design solutions while adhering to sustainable design standards.

Fire Resistant

Fire safety is important for any building project, and a fire-retardant panel is typically required in buildings that exceed a minimum height as specified by applicable codes. Alumanate FR is one of the most advanced fire-retardant materials available and meets ASTM E84, NFPA 285, CAN/ULC S102, CAN/ULC S134.

Effortless Fabrication

Alumanate ACM is easy to fabricate using ordinary wood and metalworking tools, and can be formed into complexly bent and radiused shapes. Our ACM can accommodate virtually any architectural fastening system, and are perfect for curtain wall façades, rainscreen systems, interior walls, corporate signage and more.





Color That Inspires Brilliance

Maximum brand impact comes from forming a long-lasting customer impression. Around the world, companies rely on Alumanate to amplify the visual impact of their brands. Offering long-term, cost-effective solutions for retail chains and their designers, Alumanate panels are durable, weather resistant and easy to maintain.

PVDF Kynar 500

Our paint system delivers flexibility that enables architects and designers to explore the most imaginative and eye-catching solutions. PVDF paint finishes are formulated for high UV resistance with the capability of delivering bright & vibrant colors with warranty programs up to 25 years. PVDF is simple to clean, helping to reduce the maintenance costs over the life of a brand image. Custom colors can be mixed to ensure a precise color match for any application.

Fluoropolymer Finishes

High-performing, coil-coated FEVE finishes allow color matching at the highest uniformity. Fluoropolymer technology provides excellent flexibility and film adhesion for forming, with superior resistance to humidity, impact, salt spray, pollution and abrasion. With warranty programs up to 30 years, FEVE finishes are considered the premier architectural coatings for metal.





Rigidity

Moment of Inertia

Section Modulus

Temperature Resistance (°F)

Thermal Expansion (in/ft)

Technical Data

2138 lb/in²

0.000208 in/in⁴

0.00272 in/in⁴

-55°F to 175°F

0.029 in/ft

Product Composition		
Panel Thickness (mm)	4mm	
Aluminum Skin Thickness (in)	0.020" (± 0.002")	
Core Composition	Mineral Based Fire Retardant Core	
Front Side Finish	PVDF Kynar 500 or 3-Coat FEVE	
Reverse Side Finish	Corrosion Resistant Primer Coat	
Product Characteristics		
Width (in)	48", 60", 62" (Custom Widths Available)	
Length (in)	96", 120", 144", 196" (Custom Lengths Available)	
Weight	1.55 lb/ft²	
Tolerance In Squareness (mm)	± 5mm	
Tolerance In Bow (mm)	≤ 3mm/500mm over lengths and widths	
Product Performance		





Engineering Properties

Standard Test Method*	Description	Category	4mm FR
ASTM D-635	Rate of Burning	Fire Performance Properties	Classified CC1
ASTM D-1929	Self Ignition Temperature	Fire Performance Properties	783°F
ASTM D-1929	Flash Ignition Temperature	Fire Performance Properties	784°F
ASTM E-84	Surface Burning Characteristics (Flame Spread Index)	Fire Performance Properties	0
ASTM E-84	Surface Burning Characteristics (Smoke Development Index)	Fire Performance Properties	0
CAN/ULC-S102	Surface Burning Characteristics (Smoke Development Index)	Fire Performance Properties	30
CAN/ULC-S102	Surface Burning Characteristics (Flame Spread Index)	Fire Performance Properties	0
ASTM C-365	Flatwise Compression Strength (Ultimate)	Mechanical Properties	9,220 psi
ASTM C-393	Core Shear Properties (Perpendicular) Ultimate Facing Bending Stress	Mechanical Properties	24,680 psi
ASTM C-393	Core Shear Properties (Parallel) Ultimate Facing Bending Stress	Mechanical Properties	22,460 psi
ASTM D-790	Flexural Modulus (Perpendicular)	Mechanical Properties	1,888 ksi
ASTM D-790	Ultimate Flexural (Perpendicular)	Mechanical Properties	18,521 psi
ASTM D-790	Flexural Modulus (Parallel)	Mechanical Properties	1,814 ksi
ASTM D-790	Ultimate Flexural (Parallel)	Mechanical Properties	17,688 psi
ASTM D-790	Yield Flexural Stress (Perpendicular)	Mechanical Properties	6,644 psi
ASTM D-790	Yield Flexural Stress (Parallel)	Mechanical Properties	6,923 psi
ASTM D-638	Modulus of Elasticity (Perpendicular)	Mechanical Properties	2,926 ksi
ASTM D-638	Tensile Strength (Perpendicular)	Mechanical Properties	7,725 psi
ASTM D-638	Tensile Strength at 0.20% Offset (Perpendicular)	Mechanical Properties	6,545 psi
ASTM D-638	Elongation (Perpendicular)	Mechanical Properties	14.2%
ASTM D-732	Punching Shear (Maximum Shear Load)	Mechanical Properties	2,190 lbs
ASTM D-732	Punching Shear (Shear Strength)	Mechanical Properties	4,605 psi
ASTM C-518	Thermal Conductivity	Thermal Properties	U = 6.5 btu/hr ft² °F
ASTM C-518	Thermal Resistance	Thermal Properties	R = 0.16
ASTM C-518	Thermal Conductance	Thermal Properties	6.25
ASTM D-648	Deflection Temperature (Perpendicular)	Thermal Properties	185°C
ASTM D-648	Deflection Temperature (Parallel)	Thermal Properties	189°C
ASTM C-273	Shear Test in Flatwise Plane (Ultimate Core Shear Strength)	Bond Integrity Properties	765 psi
ASTM C-297	Tensile Bond Strength Test in Flatwise Plane (Ultimate)	Bond Integrity Properties	1,009 psi
ASTM D-1781	Bond Integrity	Bond Integrity Properties	123 N mm/mm
ASTM E-90	Sound Transmission (STC)	Acoustical Properties	30
ASTM E-90	Sound Transmission (OITC)	Acoustical Properties	24
ASTM C-272	Water Absorption	Physical Properties	0.003%
ASTM D-696	Coefficient of Linear Thermal Expansion	Physical Properties	1.11x10-5 in/in °F
	-		·



Information contained herein or related hereto is intended only for evaluation by technically skilled persons, with any use thereof to be at their independent discretion and risk. Such information is believed to be reliable, but Alumanate shall have no responsibility or liability for results obtained or damages resulting from such use. Alumanate grants no license under, and shall have no responsibility or liability for infringement of, any patent or other proprietary right. Nothing in this document should be construed as a warranty or guarantee by Alumanate, and the only applicable warranties will be those set forth in Alumanate acknowledgment or in any printed warranty documents issued by Alumanate. The foregoing may be waived or modified only in writing by an Alumanate officer. Disclaimer: Laws and building and safety codes governing the design and use of Alumanate's products, and specifically aluminum composite materials, vary widely. It is the responsibility of the owner, the architect, the general contractor, the installer and the fabricator/transformer, consistent with their roles, to determine the appropriate materials for a project in strict conformity to all applicable national, regional and local building codes and regulations. ANY LABORATORY TESTING INFORMATION PROVIDED BY ALUMANATE APPLIES ONLY TO THE PARTICULAR PRODUCT OR ASSEMBLY TESTED AND DOES NOT NECESSARILY REPRESENT HOW PRODUCTS WILL ACTUALLY PERFORM IN USE.

CONTACT US:

(657) 205-6820



www.alumanate.com



info@alumanate.com 🔄



19937 Harrison Ave. City of Industry, CA 91789